

April 25, 2015

Standards Equivalency Determination

Reference: SimEx White Rigid Poly Vinyl Chloride (PVC) Exterior Profile Extrusions
ETC Laboratories Report #ETC-97-264-4091.0

I have performed an evaluation of the testing performed by ETC Laboratories in Rochester, NY in their test report ETC-97-264-4091.0. The testing was performed for AAMA and used for general qualification of white PVC material due to testing multiple manufacturers and documenting similar performance, and is therefore being submitted to qualify SimEx, Inc. white colored PVC extrusions. This is the same testing used for Miami-Dade material Master File #12-1037, the current basis for AAMA-certified extruders in the HVHZ. This report is based on older or different versions of the various ASTM standards than those referenced in the Miami-Dade Checklist #0445 and Florida Building Code 5th Edition (2014); therefore I analyzed the standards for equivalency and current code compliance. Please see the table below for the findings:

As-Tested in ETC-97-264-4091.0	As-Required in Checklist #0445 / FBC 5 th Edition (2014)	Equivalent / Meets FBC 5 th Ed. (2014)?
ASTM D1929-96 Ignition Temperature, with samples tested showing an average ignition temp. of 925°F	ASTM D1929-96(2001)e1 (this version was an ASTM re-approval of the 96 version with only editorial revisions not affecting the technical aspects of the standard), with required results of ignition temperature > 650°F	Yes
ASTM D2843-93 Smoke Density, with samples tested showing an average smoke density value of 43	ASTM D2843-99(2004)e1 (this version compared to the 93 version has identical test sample size, burner assembly and pressure, chamber size, test duration, and photometric and timing equipment) with required results of smoke density <= 75	Yes



ASTM D635-96 Rate of Burning, with samples tested all achieving a combustibility classification of Class C-1 (burn rate $\leq 1''/\text{min.}$)	ASTM D635-06 (this version compared to the 96 version has identical test duration, sample and flame size and orientation, and test apparatus, except that the wire gauze in this version is positioned more directly under the test sample to catch falling embers, which does not affect the rate of burning), with required results of Class C-1 or C-2	Yes
ASTM G26-95 Method A Xenon UV Exposure, with testing protocols of 6500W lamp, daylight filter ($0.35 \text{ W/m}^2 \cdot \text{nm}$ @ 340nm), 4500 hours, intermittent water spray.	ASTM G26 or G155 per Checklist, ASTM G155-05a per FBC: Testing complies explicitly with G26. G155-05a also requires 6500 W lamp, daylight filter ($0.35 \text{ W/m}^2 \cdot \text{nm}$ @ 340nm), 4500 hours, however FBC2010 does not require water spray. Intermittent water spray represents more stringent "torture test" of product.	Yes
ASTM D638-96 Tensile Test after G26 test exposure, with samples tested showing an average of 4.98% difference in Yield Strength between exposed and unexposed samples	ASTM D638-03 (this version compared to the 96 version has identical prescribed dog-bone geometry and tolerances, environmental pretreat and test conditions, and test speed per Table 1 of standard), with required results of change in Yield Strength of $< 10\%$	Yes


Based on these assessments, the testing performed in ETC-97-264-4091.0 is compliant with FBC 5th Edition (2014) and Miami-Dade Checklist #0445 for the standards tested.

An additional standard that is referenced in the FBC 5th Edition (2014) Section 2614.2 Approved Plastic definition, but not in the Checklist #0445, is impact testing on the samples per ASTM D256 (pendulum test) after the UV exposure. This testing is not prescribed in the Checklist #0445 because it is felt that it does not help to characterize performance changes in the samples for non-exposed vs. exposed samples, and that only the ASTM D638 testing is meaningful in this regard. As such, ASTM D256 testing was not performed in ETC-97-264-4091.0. However, an impact drop test per ASTM D4226 is performed after 6, 12, and 24 month weathering per AAMA 303, with more stringent AAMA requirements of 5340 J/m min. brittle impact results, as a prerequisite for member participation in the AAMA Fenestration Exterior Thermoplastic Profile Certification program. Because of this broad array of ongoing impact testing by AAMA members, after varying levels of exterior weathering, it is my recommendation that the ASTM D4226 testing be considered under FBC 5th Edition (2014) Sect. 104.11 as an Approved alternative to the D256 testing requirement.

Best Regards,

LT

Lucas A. Turner, P.E.
PE #58201



LT

4/25/2015

Lucas A. Turner, P.E.
FL PE #58201